

# **DATA SHEET**

SILVER 600

COD. 60490600

**Description** 

Heat resisting aluminium paint, based on a silicone resin

Use and principal characteristic

- For the protection of equipment such as furnace exteriors and heat exchangers operating from ambient temperatures up to 600°C continuous
- Good resistance to mild chemical fume environments and industrial polluted exposure.
- Fast drying, excellent gloss and colour retention

Resistance to

**Flexibility** Good

Impact resistance Very Good

Very Good **Abrasion resistance** 

Weathering Excellent

Basic data at 20°

**Colour and gloss** Aluminium - gloss

Mass density Approx. 1,10 g/cm3

Solids content by volume

Approx. 35%

Recommended dry film thickness

25- 35 micron

Coverage theoretical

14 m2/l for 25 micron

Set - to - touch

2 hour at 20°C, 4 hours at 5 - 10°C

Through dry

8 hours

Full cured

1 hour at 250°C

Overcoating interval

minimum: 12 hours at 20° C, 48 hours at 5 - 10°C

maximum: unlimited

Shelf life

12 months in cool and dry place

Shipping weight

Silver 600 60490600 18 - 4 lt 25 - 5 lt

Thinner 55100110

# Flash point (DIN 53213)

Base	26° C
Thinner	32° C

# Surface preparation and application condition

To assure a good anticorrosion protection, apply immediately after the blast cleaning a previous coat of Silicon.Zinc 55000907; dry and free from any contamination.

Steel preparation to minimum SIS- St3 can be accepted for interior exposure, but blast cleaning to ISO -Sa 2,1/2 is the minimum acceptable standard for exterior exposure.

Substrate temperature should be al least 3°C above dew point.

#### **Material preparation**

Power mixing to uniform consistency

### **Airless spray**

Recommended thinner	cod. 55100110; 0-3 %
Nozzle orifice	approx. 0,38 (=0,015 inch)
Nozzle pressure	15 MPa (= approx. 150 at 2100 p.s.i.)

#### Air spray

Recommended thinner	cod. 55100110 ; 5-10%
Nozzle orifice	1,5 - 2 mm
Nozzle pressure	0,3 MPa (= approx. 3 at 35 p.s.i.)

### Brush/Roller

cod. 55100110 at 0 - 5%. Use medium bristle brush

## **Cleaning Solvent**

cod. 55100110

#### **Additional Data**

#### SAFETY PRECAUTIONS

#### **WARNING**

VAPOUR HARMFUL, MAY CAUSE IRRITATION. COMBUSTIBLE. CONTAINS ORGANIC SOLVENTS

Avoid contact with eyes, skin and clothing. Avoid breathing vapour. Wash thoroughly after handling. Use with adequate ventilation. Wear an air supplied mask to avoid breathing concentrated vapours in enclosed areas. Close container after use.

Keep away from heat, sparks, and open flame.

In case of eye contact, immediately flush with plenty of water for al least 15 minutes.